

Duct 158 HM

PE laminated cloth tape with Hot Melt adhesive. Indispensable for water pipes and tool handles repair, area delimitation, packaging and all do-it-yourself applications.



ADVANTAGES AND PERFORMANCES

- Good adhesiveness on irregular surfaces
- Waterproof
- Removable without tearing
- Hand tearable

TECHNICAL PROPERTIES

		tolerance	test method
Backing:	PE laminated with polyester		
Adhesive:	Hot Melt		
Total weight:	110 g/m ²	± 10 %	ISO 536
Total thickness:	165 µm	± 10 %	AFERA 5006
Tensile strength:	min. 30 N/cm		AFERA 5004
Elongation at break:	min. 20 %		AFERA 5004
Adhesion to steel:	min. 5 N/cm		AFERA 5001
Temperature resistance:	room temperature		
Rolling ball tack:	max 0,5 cm		PSTC 6
Colour:	silver, black and white. Others on request		

The above values are the result of arithmetic averages from tests on sample productions and are not legally binding.

ARTICLES, DIMENSIONS AND BARCODES

	dimensions	pieces per box	barcode
Duct 158 HM silver:	50 mm x 10 m	36 rolls	8051499032456
Duct 158 HM silver:	50 mm x 25 m	24 rolls	8051499032463
Duct 158 HM silver:	50 mm x 50 m	30 rolls	8051499032470
Duct 158 HM black:	50 mm x 10 m	36 rolls	8051499032517
Duct 158 HM black:	50 mm x 25 m	24 rolls	8051499032524
Duct 158 HM black:	50 mm x 50 m	30 rolls	8051499032531
Duct 158 HM white:	50 mm x 10 m	36 rolls	8051499032487
Duct 158 HM white:	50 mm x 25 m	24 rolls	8051499032494
Duct 158 HM white:	50 mm x 50 m	30 rolls	8051499032500

OUR PROPOSAL OF PACKAGING

- Sleeve with coloured half moon label

RECOMMENDATIONS

It's a good rule to use the product within 6 months from purchase, because the unwinding force of the tape increases with time. The product must be stored in its box in a dry location protected from sunlight, at about 15 °C - 25 °C and 50% relative humidity. If stored in different conditions, the product must be reconditioned. After application, the removal of the tape must be done slowly without tears. Before applying the tape, always check if the surface is clean. Euromask disclaims any liability for any direct or indirect damage coming from the misuse of the product. Under normal conditions, the tape is not toxic and is not approved for medical use.

The a.m. values may be changed at any moment for production needs or technical updates.

rev. 01_May 2019